



Technical datasheet No.: **1663.8**

Product: POLYMAR® Scrim Sports

Article No.: 7908 5300

Type of coating and finish		
Type of coating	PVC	
Total weight	420 g/m ²	EN ISO 2286-2
Openess factor	37 %	PA 12.03 (intern)
Tensile strength warp/weft	3000 / 2300 N/50 mm	EN ISO 1421/V1
Tear strength warp/weft	700 / 400 N	DIN 53363
Cold resistance	-20 °C	EN 1876-1
High Temperature	70 °C	PA 07.04 (intern)
Translucence	36 %	at 550 nm
Light fastness	>6 Note, Value	EN ISO 105 B02
Seam strength	1000 N/50 mm	DIN 53354
for seam strength	HF weld >2cm	
Air permeability	7130 l/m ² *sec	EN ISO 9237
Base fabric		
Material	PES	DIN EN ISO 2076
Yarn count	3300 / 2200 dtex	DIN EN ISO 2060

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.